

# SERIES 5200

## Calon® Graphic Vinyl Films

# CALON

ETCHED GLASS

designed-to-application

AVAILABLE IN TWO SHADES, CALON® SERIES 5200 ETCHED GLASS IS A PREMIUM, 2-MIL CAST VINYL DESIGNED TO SIMULATE AN ETCHED GLASS OR SANDBLASTED LOOK ON A VARIETY OF SURFACES. ETCHED GLASS VINYL IS IDEAL FOR INTERIOR AND EXTERIOR APPLICATIONS ON WINDOWS, MIRRORS, PARTITIONS AND DISPLAYS. USE IT WHENEVER YOU NEED THE ADDED ELEGANCE OF AN ETCHED GLASS LOOK WITHOUT COSTLY ETCHING OR SANDBLASTING.

THIS VERSATILE PRODUCT HAS BEEN DESIGNED TO DELIVER OUTSTANDING PERFORMANCE AND DURABILITY. A UNIQUE LINER MAKES THE STANDARD ETCHED GLASS VINYL EASIER TO SEE WHEN WEEDING—EVEN WHEN USING FINE-LINED GRAPHICS AND LETTERING. AND, A SPECIAL CALON ADHESIVE SYSTEM ENSURES SUPERIOR ADHESION UNDER THE MOST DEMANDING CONDITIONS.



The Applications Are Endless

# SERIES 5200

## Calon® Graphic Vinyl Film

ETCHED GLASS

designed-to-application

### SPECIFICATIONS

#### SERIES 5200: NON-PERFORATED \*

20" x 50 yds, 24" x 50 yds  
48" x 50 yds, 60" x 50 yds

2-mil, cast vinyl simulating  
an etched glass or  
sand-blasted look

Ideal for interior and exterior  
applications on windows,  
mirrors, partitions, and displays

#### SERIES 5250: PERFORATED

15" x 50 yds  
30" x 50 yds

Outstanding performance and  
durability, superior cutting and  
weeding for improved productivity

PROPERTY	TEST METHOD	TYPICAL VALUE
SURFACE FINISH	Gloss Meter 60° Reflection	4-20 units
THICKNESS (including adhesive)	Micrometer, Federal Bench Type	.0032 in (.08 mm)
TENSILE STRENGTH	Tensile Tester with 2 in (51 mm) jaw separation, crosshead speed of 12 in/min (5.1 mm/s), web direction	≥4.5 lb/in width (≥0.8 kg/cm width)
ELONGATION	Instron tensile tester as above	≥150%
SHELF LIFE	Free from excessive moisture, temperatures, direct sunlight	2 years from factory shipment
APPLICATION TEMPERATURE RANGE	On clean substrate (optimum)	60°F to 90°F (15°C to 30°C)
HUMIDITY RESISTANCE	Applied to etched aluminum panels 24 hours prior to testing. 100% relative humidity, 100°F (38°C) for 500 hours	No appreciable effect
DIMENSIONAL STABILITY	158°F (70°C), 48 hours	0.010 - 0.020 in (0.25 - 0.50 mm)
PEEL ADHESION	PSTC-1, 15 min	60 oz/in (0.65kg/cm)
LINER RELEASE	TLMI 300 in/min (127 cm/min). 2 in (51 mm) wide sample	150 g/2 in (30 g/cm)

**ARLON SERIES 5200 WARRANTY:** Series 5200 is warranted for 7 years against excessive color loss, bubbling, cracking, and delamination when installed using recommended procedures for vertical, exterior application. Arlon materials are sold with the understanding that the buyer has independently determined the suitability of such materials. Neither the seller nor the manufacturer shall be liable for any injury, loss or damage direct or indirect arising from the use or inability to use this product. No salesman, representative, or agent is authorized to give any guarantee, warranty, or make any representation contrary to the foregoing.

\* Etched Glass 007 is only available in non-perforated profiles of 24" and 48" x 50 yards.



www.arlon.com

2811 S. Harbor Blvd  
Santa Ana, CA 92704  
Phone: (714) 540-2811 / (800) 854-0361  
Fax: (714) 540-7190 / (800) 329-2756

Badhuisweg 11  
2587 CA Den Haag  
The Netherlands  
Phone: +31 70 (0) 354-4311  
Fax: +31 70 (0) 355-7721

©Arlon 2002  
5200P 09/02