

PRODUCT INFORMATION BULLETIN

DPF 6000X Vinyl Film

With X-scape Technology

Premium Cast Digital Print Pressure Sensitive Vinyl Film

PRODUCT DESCRIPTION

DPF 6000X is a 2-mil gloss white cast film with bubble releasing, tinted, positionable, permanent pressure-sensitive adhesive. The X-scape system allows installers to achieve speedy installation while maintaining high enough tack to ensure long term bond. Designed for large format graphics, DPF 6000X is made of premium quality cast face stock with a lay-flat liner. The adhesive system is designed to provide excellent opacity, as well as easy installation. The film provides superior conformability around rivets, curves, and contours. DPF 6000X is rated for outdoor durability up to 7 years (unprinted). Printed durability is dependent on the ink system used.

AREAS OF USE

- Digital printing with a wide variety of direct print systems
- Fleet and vehicle applications
- Use in conjunction with Series 3200, 3220, 3230, or 3320 overlaminate

PERFORMANCE AND PHYSICAL DATA

<u>PROPERTY</u>	<u>TEST METHODS</u>	<u>TYPICAL VALUE</u>	
SURFACE FINISH	Gloss Meter 60° Reflection	70-90%	
THICKNESS (including adhesive)	Micrometer, Federal Bench Type	0.0032 in	0.08 mm
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 4.5 lb/in width	≥ 0.8 kg/cm width
ELONGATION	Instron Tensile Tester as above	≥ 150%	
SHELF LIFE	Free from excessive moisture, temperature, direct sunlight	2 years from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate (flat)	40°F to 100°F	4.4°C to 38°C
	On clean, dry substrate (corrugated with rivets and channels)	60°F to 100°F optimum	15°C to 38°C optimum
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-40°F to 175°F	-40°C to 79° C
DIMENSIONAL STABILITY	158°F (70°C), 48 hours	0.010 in	0.24 mm
PEEL ADHESION	PSTC-1, 15 min, RT 70°F (21°C)	≥ 2.5 lbs/in	≥ 0.45 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	80 g/2 in width	32 g/cm width

OPTIMUM PERFORMANCE

Actual weathering durability depends on surface preparation, surface maintenance and exposure conditions. Successful weather resistance is characterized by the retention of legibility.

DPF 6000 will resist weathering best when applied to vertical or upper outboard angles. Horizontal angles, such as hood and auto roof surfaces, will deteriorate more quickly than vertical. This is due to increased exposure to sun and moisture, as well as continued high deposition of dirt and atmospheric contaminants. Arlon does not recommend its film for horizontal or close horizontal applications.

ADHESION/CHEMICAL CHARACTERISTICS

ADHESION CHARACTERISTICS** SUBSTRATES	ENGLISH UNITS NOMINAL		CHEMICAL REACTION RESISTANCE		
	Lb / in width	Kg / cm	CHEMICAL AGENTS	EXPOSURE TIME	RESULTS
ETCHED ALUMINUM	4.4	0.78	TAP WATER	24 hrs	No Effect
ANODIZED ALUMINUM	5.6	1.00	ETHYLENE GLYCOL/WATER (50% Ethylene Glycol/50% water)	24 hrs	No Effect
CHROME	3.1	0.55	REFERENCE FUEL (85% Mineral Spirits/15% Xylol)	1 hr	No Effect
ACRYLIC ENAMEL	4.4	0.78	SAE 20 MOTOR OIL	24 hrs	No Effect
ACRYLIC LACQUER	4.4	0.78	JP-4 FUEL	10 mins	No Effect
ABS	5.0	0.89	10% HCL	10 mins	No Effect
			10% AMMONIUM HYDROXIDE	10 mins	No Effect
			VM & P NAPHTHA	10 mins	No Effect
			MINERAL SPIRITS	10 mins	No Effect
			METHANOL (Methyl Alcohol)	10 mins	No Effect

CONDITIONS OF SALE

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon, Inc. relating to DPF products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon, Inc. makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon, Inc. shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.



NORTH AMERICA
2811 S. Harbor Blvd
Santa Ana, CA 92704
USA

Phone: (714) 540-2811 / (800) 854-0361
Fax: (714) 540-7190 / (800) 329-2756

EUROPE
Badhuisweg 11
2587 CA Den Haag
The Netherlands
Phone: +31 (0) 70 354-4311
Fax: +31 (0) 70 355-7721